

SHEPHERD DISTRIBUTION

MOBILE FLEX  
FOLDED  
2.35 OZ/YD<sup>2</sup> MHBB  
5X5 ONE SIDE COATED

| Product Performance                                                                |                                      |
|------------------------------------------------------------------------------------|--------------------------------------|
| Physical Characteristics                                                           | Test Method                          |
| Basis Weight : 2.35 oz/yd <sup>2</sup><br>:                                        | <i>Tappi</i><br><i>T-410 om-02</i>   |
| Grab Tensile Strength : MD 100 lbs/in<br>: CD 90 lbs/in                            | <i>ASTM</i><br><i>D5034-95(2001)</i> |
| Trapezoidal Tear : MD 60 lbs<br>Strength : CD 60 lbs                               | <i>ASTM</i><br><i>D5587-03</i>       |
| Mullen Burst : 140 psi                                                             | <i>ASTM</i><br><i>D3786-01</i>       |
| Beach Puncture : Exceeds 48 inch-lbs                                               | <i>ASTM</i><br><i>D781-68</i>        |
| Outdoor exposure : Minimum 80% strength retention<br>after 1 year outdoor exposure |                                      |

Results above are typical properties for the product. They do not constitute a limiting specification for the product.