



KWANG SUNG CO., LTD

1-55 Weolam –Dong Dalseo-Gu, Daegu, Korea TEL: 82-53-582-1177 FAX: 82-53-582-1178

KS Housewrap

Repair instructions

Please follow the following guidelines for repairing damaged portions of KS House wrap.

Small Tears

For small tears (less than one inch in length), seal the tears with KS Housewrap tape or equivalent. The sheathing tape should extend a minimum of 0.75” past the edge of the tear and be applied with heavy, uniform pressure.

Large Tear and Holes

For large tears (greater than one inch in length) or holes in the building wrap, the use of a repair patch of KS Housewrap is recommended.

1. Measure and cut a piece of KS Housewrap large enough to cover the damaged area by at least six inches. Make a cut above the damaged area large enough to accommodate the patch.
2. Tuck the patch into the cut at least six inches and shingle fashion over the existing building wrap.
3. Tape along the perimeter by starting at bottom of the patch and applying a horizontal piece of KS Housewrap tape or equivalent that extends at least two inches past the side of the patch. Apply the remaining tape in shingle fashion, beginning with the side of the patch and finishing with the top horizontal portion.